Contribution ID: 284

Type: poster

## High-temperature precipitate microstructure and misfit in Inconel-type superalloy

Thursday 19 September 2013 12:30 (2 hours)

Nickel base superalloys are a natural composites consisting of  $\gamma$  precipitates (L12) with an ordered structure coherently embedded in a  $\gamma$  solid solution (fcc) matrix. The critical parts of turbines made of Ni-based superalloy are subjected to cyclic elastic-plastic straining as a result of heating and cooling during start-up and shut-down periods. Consequently, low-cycle fatigue at operating temperatures (up to 900°C) is an important factor in the evaluation of the service life. The thermo-mechanical exposure during low-cycle fatigue is connected with a change of its microstructure, namely the size and distribution of precipitates. Moreover, an important parameter for the characterization of microstructural changes in nickel base superalloys is misfit - the relative difference between lattice parameters of  $\gamma$  matrix and  $\gamma'$  precipitates.

Nickel base superalloy IN738LC has been studied after low-cycle fatigue by small-angle neutron scattering (SANS) and neutron diffraction (ND) at SINQ (SANS-II and POLDI facilities).

Samples subjected to high-temperature low-cycle fatigue were annealed at various temperatures to change the size and the distribution of precipitates. Ex- and in-situ SANS and high resolution TEM studies were performed. It was found that additional precipitates are produced either during slow cooling from high temperatures or after reheating above 570°C. Their size and distribution were evaluated. The precipitates arise regardless the application of the mechanical load. Nevertheless, these small precipitates influence low-cycle fatigue resistance. From the SANS data, it can be also deduced that the equilibrium volume fraction of  $\gamma'$ -precipitates at temperatures from room temperature to 825°C is significantly higher than 45%. The kinetics of formation of small and medium-size  $\gamma'$ precipitates at 700 and 800°C was determined as well.

Misfit in IN738LC superalloy was examined at POLDI TOF neutron diffractometer both ex-situ and in-situ at elevated temperatures. A careful out-of-furnace measurement yielded the lattice parameters of both  $\gamma$  and  $\gamma'$  phases at room temperature (a $\gamma$ = 3.58611(10) Å, a $\gamma'$ = 3.58857(17) Å) as well as misfit (equal to 6.9(6)×10-4). The in-situ measurement at elevated temperatures determined the temperature dependence of lattice parameters of  $\gamma$  (up to 1120°C) and  $\gamma'$ (up to 1000°C). Using these data, evolution of the misfit with temperature was calculated. The misfit decreases with increasing temperature until it reaches zero value at temperature around 800°C. Above 800°C, it becomes negative.

The support by GACR project No. P204/11/1453 and NMI3-II EC infrastructural project No. 283883 are ac-knowledged.

Author: Dr STRUNZ, Pavel (Nuclear Physics Institute, CZ-25068 Rez near Prague)

**Co-authors:** SAROUN, J (1Nuclear Physics Institute, CZ-25068 Rez near Prague, Czech Republic); TOBIAS, J (IPM Brno, Czech Republic); PETRENEC, M (IPM and TESCAN a.s. Brno, Czech Republic); BERAN, P (1Nuclear Physics Institute, CZ-25068 Rez near Prague, Czech Republic); Dr GASSER, Urs Gasser (Laboratory for Neutron Scattering, Paul Scherrer Institut); DAVYDOV, Vadim (Paul Scherrer Institut)

Presenter: Dr STRUNZ, Pavel (Nuclear Physics Institute, CZ-25068 Rez near Prague)

Session Classification: Poster session II and lunch