

## Evidence for large electric polarization from collinear magnetism in $\text{TmMnO}_3$

V Yu Pomjakushin<sup>1</sup>, M Kenzelmann<sup>1,2</sup>, A Dönni<sup>3</sup>, A B Harris<sup>4</sup>,  
T Nakajima<sup>5</sup>, S Mitsuda<sup>5</sup>, M Tachibana<sup>3</sup>, L Keller<sup>1</sup>, J Mesot<sup>1</sup>,  
H Kitazawa<sup>3</sup> and E Takayama-Muromachi<sup>3</sup>

<sup>1</sup> Laboratory for Neutron Scattering, ETH Zürich & Paul Scherrer Institute, CH-5232 Villigen, Switzerland

<sup>2</sup> Laboratory for Solid State Physics, ETH Zürich, CH-8093 Zürich, Switzerland

<sup>3</sup> National Institute for Materials Science (NIMS), 1-2-1 Sengen, Tsukuba, Ibaraki 305-0047, Japan

<sup>4</sup> Department of Physics and Astronomy, University of Pennsylvania, Philadelphia, PA 19104, USA

<sup>5</sup> Department of Physics, Faculty of Science, Tokyo University of Science, Kagurazaka 1-3, Shinjuku-ku, Tokyo, Japan  
E-mail: [michel.kenzelmann@psi.ch](mailto:michel.kenzelmann@psi.ch)

*New Journal of Physics* **11** (2009) 043019 (9pp)

Received 22 January 2009

Published 15 April 2009

Online at <http://www.njp.org/>

doi:10.1088/1367-2630/11/4/043019

**Abstract.** There has been tremendous research activity in the field of magneto-electric (ME) multiferroics after Kimura *et al* (2003 *Nature* **426** 55) showed that antiferromagnetic and ferroelectric orders coexist in orthorhombically distorted perovskite  $\text{TbMnO}_3$  and are strongly coupled. It is now generally accepted that ferroelectricity in  $\text{TbMnO}_3$  is induced by magnetic long-range order that breaks the symmetry of the crystal and creates a polar axis (Kenzelmann *et al* 2005 *Phys. Rev. Lett.* **95** 087206). One remaining key question is whether magnetic order can induce ferroelectric polarization that is as large as that of technologically useful materials. We show that ferroelectricity in orthorhombic (o)  $\text{TmMnO}_3$  is induced by collinear magnetic order, and that the lower limit for its electric polarization is larger than in previously investigated orthorhombic heavy rare-earth manganites. The temperature dependence of the lattice constants provides further evidence of large spin–lattice coupling effects. Our experiments suggest that the ferroelectric polarization in the orthorhombic perovskites with

commensurate magnetic ground states could pass the  $1 \mu\text{C cm}^{-2}$  threshold, as predicted by theory (Sergienko *et al* 2006 *Phys. Rev. Lett.* **97** 227204; Picozzi *et al* 2007 *Phys. Rev. Lett.* **99** 227201).


Multiferroic materials are defined as materials with more than one switchable spontaneous order parameter such as ferromagnetism and ferroelectricity. It has become custom to include materials with coexisting spontaneous antiferromagnetic and ferroelectric order in the class of magneto-electric (ME) multiferroics. One can distinguish two major classes of ME multiferroics: those where the onset of ferroelectricity is unrelated to magnetic order, and those where ferroelectricity is induced by magnetic order. Hexagonal YMnO<sub>3</sub> is an example of a multiferroic material where the onset of ferroelectricity is completely unrelated to the onset of magnetism, and probably arises from geometrical effects [5]. Orthorhombic TbMnO<sub>3</sub> is an example of a multiferroic material where ferroelectricity arises from magnetic spiral order [1, 2]. Ferroelectricity from magnetic order is related to competing magnetic interactions, whose competition at low temperatures is reduced through small lattice distortions that result in switchable electric polarization.

Magnetically induced ferroelectricity has been observed for structurally very different materials, most notably in rare-earth (R) manganites RMn<sub>2</sub>O<sub>5</sub> [6], the kagome staircase magnet Ni<sub>3</sub>V<sub>2</sub>O<sub>8</sub> [7] and the triangular lattice antiferromagnet RbFe(MoO<sub>4</sub>)<sub>2</sub> [8]. This suggests that the mechanism to obtain ferroelectricity from magnetic order is quite general and should be present in many materials. In all these materials, ferroelectric polarization arises, at least partly, from incommensurate spiral magnetic structures that lead to polar structures. The ME interaction in these materials is believed to be mediated by spin-orbit interactions, and so the ferroelectric polarization is relatively small.

Much larger ferroelectric polarizations were predicted for materials where ferroelectricity arises from *collinear* magnetic order [3, 4]. In such materials, ME coupling may be mediated by the symmetric exchange, which is larger than spin-orbit related interactions. An example is orthorhombic (o) HoMnO<sub>3</sub> where ferroelectricity arises from commensurate, collinear magnetic order [9, 10]. However, the ferroelectric polarization in o-HoMnO<sub>3</sub> was observed to be much smaller than predicted [4], and arises partly from rare-earth magnetic order [9]. Here, we present the case of o-TmMnO<sub>3</sub> for which we observed a ferroelectric polarization that arises from collinear Mn<sup>3+</sup> magnetic order, and that is at least 15 times larger than observed for o-HoMnO<sub>3</sub>. We provide evidence for spin-lattice coupling effects that are larger than in other magnetically induced ferroelectrics.

Polycrystalline samples of perovskite TmMnO<sub>3</sub> were prepared under high pressure as described in [11]. Neutron powder diffraction measurements were performed on a large amount (5.4 g) of TmMnO<sub>3</sub> sample using the HRPT [12] and DMC diffractometers at the Paul Scherrer Institute, and incident neutrons with a wavelength of 1.89 and 4.5 Å, respectively. The magnetic structures were determined using the Fullprof Suite [13]. No texture effects were observed during the analysis.


The ferroelectric polarization was determined using a 0.4 mm thin hardened pellet of polycrystalline TmMnO<sub>3</sub> covered with an area  $3.12 \times 10^{-6} \text{ m}^2$  of silver epoxy. The sample was cooled from 50 to 2 K in poling electric fields of up to  $E = 3750 \text{ kV m}^{-1}$ , after which the electric field was reduced to zero and the sample was allowed to discharge for 5 min. After the discharge at 2 K the residual current was reduced to  $10^{-14} \text{ A}$ , which suggests that trapped charges did not affect the pyroelectric measurement. Then the sample was heated at different constant rates



**Figure 1.** Chemical structure of  $\text{TmMnO}_3$ , showing  $\text{Mn}^{3+}$  in red and  $\text{O}^{2-}$  in blue. (a) Incommensurate amplitude-modulated  $\text{Mn}^{3+}$  spin order in the paraelectric phase for  $32 \text{ K} < T < 40 \text{ K}$ . (b, c) Commensurate  $\text{Mn}^{3+}$  spin order of  $E_1$  and  $E_2$  types respectively, in the ferroelectric phase for  $T \ll 32 \text{ K}$ . The large arrows show the direction of the spontaneous polarization along the  $c$ -axis that arises from a movement of the  $\text{Mn}^{3+}$  and  $\text{O}^{2-}$  positions (shown here schematically) to adjust the Mn–O–Mn angle for parallel and antiparallel nearest-neighbor alignments, thereby lowering symmetry through the creation of a polar axis. (a–c) The moments in the neighboring planes are oriented in the opposite direction.

between  $0.85$  and  $4.86 \text{ K min}^{-1}$  and the pyroelectric current was measured using a Keithley 6517A electrometer, resulting in nearly identical estimates of the ferroelectric polarization. Pyroelectric measurements at different ramping speeds and a stop-and-go ramp result in a nearly identical temperature-dependent electric polarization, showing the thermal excitation of trapped charges does not affect the pyroelectric measurements. These measurements therefore allow the determination of the lower limit of the electric polarization. Real and imaginary parts of the dielectric constant were measured using an Agilent E4980A LCR meter, making sure that the Maxwell–Wagner effect does not affect the measurements. The magnetic susceptibility was measured in an external field  $H = 100 \text{ Oe}$  on a small ( $5.9 \text{ mg}$ ) powder sample using a Quantum Design SQUID magnetometer.


$\text{TmMnO}_3$  crystallizes in the space group  $\text{Pnma}$  and has room-temperature lattice parameters  $a = 5.809 \text{ \AA}$ ,  $b = 7.318 \text{ \AA}$  and  $c = 5.228 \text{ \AA}$ . A projection of the crystal structure onto the  $ac$  plane is shown in figure 1. The unit cell contains four  $\text{Mn}^{3+}$  ions, located at  $\mathbf{r}_1 = (0, 0, 0.5)$ ,  $\mathbf{r}_2 = (0.5, 0.5, 0)$ ,  $\mathbf{r}_3 = (0.5, 0, 0)$  and  $\mathbf{r}_4 = (0, 0.5, 0.5)$ . The large rotation of the oxygen octahedra around the  $\text{Mn}^{3+}$  ions is expected to result in appreciable antiferromagnetic superexchange interactions along the  $a$ -axis through pairs of oxygen anions [14] that compete with the ferromagnetic interactions in the  $ac$  plane.



**Figure 2.** Part of the neutron scattering patterns measured using HRPT, as a function of scattering angle  $2\Theta$  at (a)  $T = 50$  K showing only nuclear scattering, and (b)  $T = 2$  K showing additionally magnetic scattering. (c, d) Bragg peak powder patterns measured using DMC at  $T = 35$  and  $2$  K. (a–d) The vertical bars indicate magnetic and nuclear (upper row) Bragg peaks. The bottom solid line indicates the difference between the experiment and the model.

Our neutron diffraction data, shown in figure 2, feature new Bragg peaks below  $T_N^{\text{Mn}} = 42$  K and demonstrate that  $\text{TmMnO}_3$  adopts magnetic order below  $T_N^{\text{Mn}}$ . The ordering wavevector is  $\mathbf{Q} = (q, 0, 0)$ , where  $q$  is the modulation wavenumber along the  $a$ -axis. The temperature dependence of the magnetic neutron Bragg peaks indicates a second-order transition at  $T_N^{\text{Mn}}$ , as shown in figure 3, and an anomaly at  $T_C = 32$  K indicates a further transition. These two transitions coincide with peaks in the temperature dependence of the specific heat [11]. The temperature dependence of the magnetic peaks close to  $\mathbf{Q} = (0.5, 1, 0)$  (figure 3(c)) shows that the magnetic structure is incommensurate for  $T_C < T < T_N^{\text{Mn}}$  and commensurate for  $T < T_C$ . In the incommensurate phase, the ordering wavevector is  $\mathbf{Q} = (q, 0, 0)$  with  $0.45 < q \leq 0.5$ .

The incommensurate magnetic order is described by one single-order parameter with an amplitude given by  $\mathbf{m}_{\text{IC}}^1 = \sqrt{2} (2.11(1), 0.0(3), 0.67(2))\mu_B$  of the  $\text{Mn}^{3+}$  ions at  $T = 35$  K, and so it is slightly different from the incommensurate order in  $\text{HoMnO}_3$  that is collinear [10]. No magnetic order was detected on the  $\text{Tm}^{3+}$  ions in the incommensurate phase. Experimentally, we cannot determine the phase difference between the  $a$  and  $c$  components of  $\mathbf{m}_{\text{IC}}^1$ . However,



**Figure 3.** (a) Temperature dependence of the magnetic Bragg peak intensity at  $\mathbf{Q} = (0.5, 1, 0)$  in the commensurate phase, or the added intensities at the  $\mathbf{Q} = (q, 1, 0)$  and  $\mathbf{Q} = (1 - q, 1, 0)$  Bragg peak positions for  $0.45 < q \leq 0.5$ . (b) Comparison of the temperature dependence of different magnetic Bragg peaks, showing that they have the same temperature dependence in the commensurate phase. The  $\mathbf{Q} = (1.5, 0, 1)$  Bragg peak is only present in the commensurate phase, and is evidence of the ordering of  $\text{Tm}^{3+}$  magnetic moments. (c) Temperature dependence of the  $a$ -component,  $h$ , of the magnetic Bragg peak  $\mathbf{Q} = (h, 1, 0)$ , where  $h = q$  or  $1 - q$ . (d) Temperature dependence of the magnetic correlation length as deduced from the width of the magnetic Bragg peaks.

because the magnetic basis vectors have to respect the inversion center of the paramagnetic phase, it can be shown that the  $a$  and  $c$  components of  $\mathbf{m}_{\text{IC}}^1$  have the same phase [16]. The incommensurate structure is thus amplitude-modulated with moments at an angle to the  $a$ -axis, as shown in figure 1(a).

The commensurate structure at  $T = 2$  K is described by the two-dimensional order parameter as specified below. The magnetic order is an  $E$ -type magnetic structure shown in figures 1(b) and (c), with  $3.75(3)\mu_{\text{B}}$  magnetic moment ordered on the  $\text{Mn}^{3+}$  sites along the  $a$ -axis. The  $E$ -type magnetic structure can have two independent basis vectors for the moments along the  $a$ -axis:  $E_1 = (1, 1, -1, -1)$  and  $E_2 = (1, -1, 1, -1)$  in the order of the  $\text{Mn}^{3+}$  ion as defined above—identical to the low-temperature  $\text{Mn}^{3+}$  order in  $\text{HoMnO}_3$  [10]. In addition, we found that  $\text{Tm}^{3+}$  has an ordered moment of  $1.22(5)\mu_{\text{B}}$  pointing along the  $c$ -axis at 2 K. Because the  $\text{Tm}^{3+}$  moments are allowed only along the  $b$ -axis if they were magnetically polarized by

the  $\text{Mn}^{3+}$  order, this implies that the  $\text{Tm}^{3+}$  undergo independent spontaneous magnetic order, as indicated by a peak in the specific heat at around  $T_N^{\text{Tm}} = 4 \text{ K}$  [11].

From the group theory point of view, the incommensurate magnetic structure belongs to irreducible representation  $\Gamma_{\text{IC}}^3$ , where the superscript corresponds to Kovalev's notation [15], and is defined by the following characters:  $\chi(I) = 1$ ,  $\chi(2_a) = -\alpha$ ,  $\chi(m_{ab}) = -\alpha$  and  $\chi(m_{ac}) = 1$ , with  $\alpha = \exp(i\pi q)$ . Here,  $2_a$  is a two-fold screw axis rotation, whereas  $m_{ab}$  and  $m_{ac}$  are  $ab/ac$ -mirror planes followed by a  $(0.5, 0, 0.5)$  or  $(0, 0.5, 0)$  lattice translation, respectively. The commensurate structure at  $T = 2 \text{ K}$  is described by the two-dimensional irreducible representation  $\Gamma_{\text{C}}^1$  according to Kovalev's notation and defined by the following nonzero characters:  $\chi(I) = 2$  and  $\chi(m_{ac}) = -2$ .


Figure 4(a) shows that  $\text{TmMnO}_3$  has a macroscopic response to the onset of magnetic long-range order and develops spontaneous electric polarization  $P$  below 32 K, demonstrating that o- $\text{TmMnO}_3$  has a multiferroic ground state. The observed value of  $P$  for a powder sample,  $P = 1500 \mu\text{C m}^{-2}$ , is more than 15 times larger than that of o- $\text{HoMnO}_3$  [9]. The value of  $P$  for a powder sample is half the intrinsic value for a single crystal, namely  $P_0 = 0.3 \mu\text{C cm}^{-2}$ . Since we have not observed the saturation of  $P(E)$ , as shown in the inset of figure 4(a),  $P_0$  may be substantially higher and our observation is a lower limit of the intrinsic polarization. The reported electric polarization in o- $\text{HoMnO}_3$  was much smaller, so our results suggest that sample quality or the details of the crystal structure are decisive for the size of the electric polarization in the orthorhombic rare earth manganites. The experimentally observed polarization, that is merely a lower limit for the intrinsic electric polarization, is the highest value for magnetically induced ferroelectricity, and is entirely consistent with the predicted  $P_0 = 0.5\text{--}12 \mu\text{C cm}^{-2}$  [3] and  $6 \mu\text{C cm}^{-2}$  [4] that are higher by a factor of 1.7–40. This is strong experimental evidence for the validity of the theoretically predicted electric polarization, and the strongest evidence to date that symmetric spin exchange can give rise to magnetically induced ferroelectricity that is large enough for applications.

From the magnetic structures shown in figure 1, we propose a likely scenario for the magnetic exchange interactions in  $\text{TmMnO}_3$ . These structures suggest that the interactions between second neighbors are ferromagnetic along the  $c$ -axis and are antiferromagnetic along the  $a$ - and  $b$ -axes. In the commensurate phase (for  $T < T_C$ ) the distortion of the nearest-neighbor bonds is such that the straighter bonds have an interaction that is less ferromagnetic (or more antiferromagnetic) than the bent bonds, thus removing the frustration that would occur in the absence of the distortion. For  $T_C < T$ , when the bonds are undistorted, the frustration is removed by the incommensurate structure of figure 1(a).

The magnetic order is never strictly long range, because magnetic Bragg peaks were found to be always wider than the resolution-limited nuclear Bragg peaks. Figure 3(d) shows that the magnetic correlation length never exceeds 600 nm, and most probably arises from ferroelectric domains. Picozzi *et al* [4] showed that ferroelectric polarization in  $\text{HoMnO}_3$  is generated mostly through movements of the  $\text{Mn}^{3+}$  and  $\text{O}^{2-}$  positions, so the magnetic structure  $E_1$  and  $E_2$  (shown in figure 1) favor opposite ferroelectric polarization, as can be seen from the phenomenological formula  $P_0 \propto (E_1^2 - E_2^2)$ . Thus the magnetic structure  $E_1$  and  $E_2$  must be separated by magnetic domain walls, limiting the magnetic correlation length to the size of the ferroelectric domains. Our measurements thus suggest that the magnetic domains can be controlled by electric fields.

The temperature dependence of the real part of the dielectric susceptibility, shown in figure 4(c), provides evidence for the ferroelectric transition at  $T_C = 32 \text{ K}$ , in agreement with the pyroelectric measurements. The imaginary part of the dielectric constant, shown in






**Figure 4.** (a) Electric polarization of a pressed powder sample of o-TmMnO<sub>3</sub> as a function of temperature, determined using pyroelectric measurements after cooling an electrically poled sample. Inset: electric polarization at  $T = 2$  K as a function of poling electric field with which the sample was cooled. (b) Magnetic susceptibility as a function of temperature measured on cooling. Inset: temperature derivative of the magnetic susceptibility indicating the onset of spontaneous Tm<sup>3+</sup> magnetic order at  $T_N^{\text{Tm}} = 4$  K. (c) Real and (d) imaginary parts of the dielectric susceptibility as a function of temperature, measured at a frequency of  $f = 100$  kHz.

figure 4(d), shows a two-peak feature as a function of temperature, and relatively high values between  $T_N^{\text{Tm}} = 4$  K and  $T_C = 32$  K that suggest substantial energy dissipation. The energy dissipation in this temperature range may result from slow switching behavior associated with the magnetically polarized Tm<sup>3+</sup> magnetic moments that are only loosely coupled to the rapidly switching Mn<sup>3+</sup>. Below  $T_N^{\text{Tm}} = 4$  K, the Tm<sup>3+</sup> moments are spontaneously ordered and therefore not directly connected with the electric order, so that dielectric constant shows no dissipation, as shown in figure 4(d). This scenario is also consistent with the flattening off of the electric polarization stopping below  $T_N^{\text{Tm}} = 4$  K, suggesting that the Tm<sup>3+</sup> order competes with the Mn<sup>3+</sup> order and thereby limits the size of the electric polarization.

Independent evidence for strong coupling between the chemical and magnetic lattice is also seen in the temperature dependence of the lattice constants, shown in figure 5. These spin–lattice effects are larger than in any other heavy rare-earth o-RMnO<sub>3</sub>, suggesting that the magnetic order has a stronger effect on the chemical lattice of o-TmMnO<sub>3</sub> than in other heavy rare-earth manganites. Our results can be understood phenomenologically as follows. Because



**Figure 5.** Temperature dependence of the lattice constants for  $T < 50$  K. The insets show additional transitions below 4 K. The vertical dotted lines at  $T_N^{\text{Mn}}$  and  $T_C$  indicate magnetic transitions, whereas the vertical dotted line at  $T_N^{\text{Tm}} = 4$  K indicates the onset of spontaneous  $\text{Tm}^{3+}$  magnetic order.

the incommensurate magnetic order is described by only a single one-dimensional order parameter, there can be no magnetically induced ferroelectricity in accordance with our experiment [16]. In the commensurate phase, the ME interaction is of the form given in [3]. However, the fourth order terms in the magnetic free energy cause either  $E_1 \cdot E_2 = 0$  or  $|E_1| = |E_2|$ , depending on the sign of the fourth order spin anisotropy [17]. Thus the higher order ME interaction in [3] is generally inoperative and the polarization is restricted to lie along the  $c$ -axis with magnitude  $P_c \propto (E_1^2 - E_2^2)$ , where  $E_1 E_2 = 0$  is selected. The temperature dependence of  $P$  is only qualitatively consistent with this, possibly because the results are somewhat modified by the sample not being a single crystal.

In summary, we have shown that  $\text{TmMnO}_3$  has a magnetically induced electric polarization that is substantially higher than in any other heavy rare-earth manganites with commensurate magnetic order. We observed anomalies in the temperature dependence of the lattice constants at the magnetic phase transitions that are evidence for strong coupling effects between the chemical and magnetic lattices. Theoretical calculations have predicted a large spontaneous electric polarization in  $\text{HoMnO}_3$ , at variance with current experimental results [4]. Since we have found such a large polarization in  $\text{TmMnO}_3$ , it is of great interest to have such calculations done for this system and hopefully to understand the difference between  $\text{HoMnO}_3$  and  $\text{TmMnO}_3$ .



## Acknowledgments

We acknowledge valuable discussions with R A Cowley, N A Spaldin, and D Khomskii. This work was supported by the Swiss NSF (contract no. PP002-102831). This work is based on experiments performed at the Swiss spallation neutron source SINQ, Paul Scherrer Institute.

## References

- [1] Kimura T, Goto T, Shintani H, Ishizaka K, Arima T and Tokura Y 2003 Magnetic control of ferroelectric polarization *Nature* **426** 55
- [2] Kenzelmann M, Haris A B, Jonas S, Broholm C, Schefer J, Kim S B, Zhang C L, Cheong S W, Vajk O P and Lynn J W 2005 Magnetic inversion symmetry breaking and ferroelectricity in  $\text{TbMnO}_3$  *Phys. Rev. Lett.* **95** 087206
- [3] Sergienko I A, Sen C and Dagotto E 2006 Ferroelectricity in the magnetic e-phase of orthorhombic perovskites *Phys. Rev. Lett.* **97** 227204
- [4] Picozzi S, Yamauchi K, Sanyal B, Sergienko I A and Dagotto E 2007 Dual nature of improper ferroelectricity in a magnetoelectric multiferroic *Phys. Rev. Lett.* **99** 227201
- [5] Van Aken B B, Palstra T T M, Filippetti A and Spaldin N A 2004 The origin of ferroelectricity in magnetoelectric  $\text{YMnO}_3$  *Nat. Mater.* **3** 164
- [6] Hur N, Park S, Sharma P A, Ahn J S, Guha S and Cheong S W 2004 Electric polarization reversal and memory in a multiferroic material induced by magnetic fields *Nature* **429** 392
- [7] Lawes G *et al* 2005 Ferroelectricity through magnetic inversion symmetry breaking on a kagome staircase *Phys. Rev. Lett.* **95** 087205
- [8] Kenzelmann M *et al* 2007 Direct transition from a disordered phase to an incommensurate multiferroic on a triangular lattice *Phys. Rev. Lett.* **98** 267205
- [9] Lorenz B, Wang Y Q and Chu C W 2007 Ferroelectricity in perovskite  $\text{HoMnO}_3$  and  $\text{YMnO}_3$  *Phys. Rev. B* **76** 104405
- [10] Munoz A, Casais M T, Alonso J A, Martinez-Lope M J, Martinez J L and Fernandez-Diaz M T 2001 Complex magnetism and magnetic structures of the metastable  $\text{HoMnO}_3$  perovskite *Inorg. Chem.* **40** 1020
- [11] Tachibana M, Shimoyama T, Kawaji H, Atake T and Takayama-Muromachi E 2007 Jahn–Teller distortion and magnetic transitions in perovskite  $\text{RMnO}_3$  ( $R = \text{Ho, Er, Tm, Yb}$  and  $\text{Lu}$ ) *Phys. Rev. B* **75** 144425
- [12] Fischer P *et al* 2000 High resolution powder diffractometer HRPT for thermal neutrons at SINQ *Physica B* **276–278** 146
- [13] Rodriguez-Carvajal J *The FullProf Suite* <http://www.ill.eu/sites/fullprof/>  
Rodriguez-Carvajal J 1993 Recent advances in magnetic structure determination by neutron powder diffraction *Physica B* **192** 55
- [14] Kimura T, Ishihara S, Shintani H, Arima T, Takahashi K T, Ishizaka K and Tokura Y 2003 Distorted perovskite with  $e_g^1$  configuration as a frustrated spin system *Phys. Rev. B* **68** 060403
- [15] Kovalev O V 1993 *Representations of the Crystallographic Space Groups* ed H T Stokes and D M Hatch (London: Gordon and Breach)
- [16] Harris A B 2007 Landau analysis of the symmetry of the magnetic structure and magnetoelectric interaction in multiferroics *Phys. Rev. B* **76** 054447
- [17] Harris A B, Aharony A and Entin-Wohlman O 2008 Order parameters and phase diagram of multiferroic  $\text{RMn}_2\text{O}_5$  *Phys. Rev. Lett.* **100** 217202