

Why does an almost pure-beryllium alloy exhibit a hundred-fold increase in T_c ?

Wednesday, 30 October 2019 15:40 (20 minutes)

As one of the lightest elements, beryllium exhibits high-frequency lattice vibrations, a condition for achieving superconductivity (SC) with a sizeable critical temperature. Yet, paradoxically, its $T_c = 0.026$ K is so low, that its SC is often overlooked. Clearly, T_c is affected also by other factors, notably the electron-phonon coupling strength and the density of states (DOS) at the Fermi level $N(\varepsilon_F)$ (rather low in pure Be). Recently, computational searches have shown that SC is more likely to occur in p^0 - and d^1 metals with low-lying empty orbitals. Their electronic properties are predicted to be highly sensitive to structural details, thus resulting in stronger electron-phonon interactions and higher $N(\varepsilon_F)$ [1]. Based on this intuition, Be-rich alloys may achieve a much higher T_c than elementary Be itself, a prediction which turns out to be true for ReBe₂₂, whose $T_c \sim 9.6$ K [2] exceeds by almost 400(!) times that of Be. Here, we report on an extensive study of the physical properties in the normal- and superconducting state of ReBe₂₂, by using a series of experimental techniques, in particular muon-spin rotation/relaxation (μ SR), as well as numerical density-functional-theory (DFT) band-structure calculations [3]. Our results not only explain the origin of the formidable increase of T_c in ReBe₂₂, but also predict exciting developments in case of chemical substitution (of Re with Mo or W) or under high-pressure conditions.

1. D. V. Semenov, A. G. Kvashnin, I. A. Kruglov, and A. R. Oganov, *J. Phys. Chem. Lett.* **9**, 1920 (2018).
2. E. Bucher and C. Palmy, *Phys. Lett. A* **24**, 340 (1967).
3. T. Shang et al., *New J. Phys.* **21**, 073034 (2019).

Position

Scientist

Primary authors: SHIROKA, T. (Paul Scherrer Institut); SHANG, T. (Paul Scherrer Institut); AMON, A. (MPI CPS); KASINATHAN, D. (MPI CPS); XIE, W. (Zhejiang Univ.); BOBNAR, M. (MPI CPS); CHEN, Y. (Zhejiang Univ.); WANG, A. (Zhejiang Univ.); SHI, M. (Paul Scherrer Institut); MEDARDE, M. (Paul Scherrer Institut); YUAN, H.-Q. (Zhejiang Univ.)

Presenter: SHIROKA, T. (Paul Scherrer Institut)

Session Classification: Contributed talks

Track Classification: Oral presentation