

Elucidation of the complex (de-)lithiation reactions of SnO_2 in all-solid-state battery using operando X-ray photoelectron spectroscopy

Tuesday, 29 October 2019 17:05 (5 minutes)

For the successful employment of Li-ion batteries at large scale, e.g. for electrical vehicles or stationary energy storage, a crucial point is to increase of energy density in the battery. In order to increase this parameter, anode conversion-alloy materials, such as SnO_2 with a specific capacity of $\sim 1500 \text{ mAh/g}$, are a serious choice, in particular when mixed with graphite. Despite the theoretical predictions of the different SnO_2 conversion and alloy reactions during (de-)lithiation, the experimental identification of those electrochemical reactions and the formation of intermediate species (e.g. Li_xSnO_y , Li_xSn and Li_2O) is not fully understood,¹ mainly due to their possible relaxation and conversion to other byproducts during disassembling of the cycled cell in *post mortem* analysis.²

In this contribution we explore the capabilities of our recently developed *operando* X-ray photoelectron spectroscopy (o-XPS) to monitor in real time the evolution of the electrolyte-electrode interface and the (de-)lithiation processes of the active materials during solid state Li-ion battery operation.³ In particular, we present the results of our study on the (de-)lithiation of the SnO_2 particles in a working electrode composed of SnO_2 nanoparticles, $(\text{Li}_2\text{S})_3\text{-P}_2\text{S}_5$ (LPS)⁴ solid electrolyte (SE) and Super P as conductive carbon cycled versus InLi_x counter electrode (Figure 1a). The analysis of the Sn 3d (Figure 1b), Sn 4d, O 1s (Figure 1c) and Li 1s spectra reveals the progressive conversion of the SnO_2 particles to form Sn^0 and the simultaneous formation of the Li_xSn alloy. When the potential is below 0.4 V (vs. Li^+/Li), the Li_2O phase is formed and grows until the full lithiation at 0.01 V (vs. Li^+/Li), where the only species observed are Li_2O and Li_xSn . During the de-lithiation process, the partial reversibility of the conversion-alloy reactions takes place, where Li_xSn is converted to SnO_x at 2.5 V (vs. Li^+/Li). The S 2p and P 2p core levels reveal the presence of reduced Li_2S byproduct species below 1.6 V (vs. Li^+/Li), in accordance with previous studies.⁴

References:

- [1] Y. Cheng, A. Nie, L.-Y. Gan, Q. Zhang, U. Schwingenschlögi, *J. Mater. Chem. A*, **2015**, 3, 19483
- [2] G. Ferraresi, C. Villevieille, I. Czekaj, M. Horisberger, P. Novák, M. El Kazzi, *ACS Appl. Mater. Interfaces*, **2018**, 10, 8712-8720
- [3] X. Wu, C. Villevieille, P. Novák, M. El Kazzi, *Phys. Chem. Chem. Phys.*, **2018**, 20, 11123
- [4] X. Wu, M. El Kazzi, C. Villevieille, *J. Electroceram.*, **2017**, 38, 207-214

Position

Phd

Primary authors: MIROLO, Marta (PSI - Paul Scherrer Institut); WU, Xiaohan (Paul Scherrer Institut); VAZ, Carlos (Paul Scherrer Institut); NOVÁK, Petr (Paul Scherrer Institut); EL KAZZI, Mario (Paul Scherrer Institut)

Presenter: MIROLO, Marta (PSI - Paul Scherrer Institut)

Session Classification: Flash talks

Track Classification: Flash talks